

TEST REPORT

313311 / 1

Revision: 0
Date of receipt: 28/06/21
Date of test: 06/07/21
Date of issue: 06/07/21

Sample name: GREEN COLLECTION

ALFATEX ITALIA S.R.L.
VIA LIGURIA, ZONA PIP
70029 SANTERAMO IN COLLE (BA)
ITALIA

California Technical Bulletin 117:2013 (Section 1 - Cover material test)

The test has been carried out in accordance with Section 1 of California Technical Bulletin 117:2013 - "Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture"

Description of cover material as declared by the client

- material: art. "GREEN COLLECTION" produced by ALFATEX ITALIA SRL Company.

Standard materials supplied by Laboratory in accordance with the specifications described in Annex B

- standard polyurethane foam substrate;
- standard cotton sheeting material.

Conditioning

At least 24 hours at 21 ± 3 °C temperature and less than 55 % relative humidity.


Application	Char length on vertical panel approx. to nearest 2,5 mm (Requirement: ≤ 45 mm)	Self-extinguished cigarette (Yes/No)	Smouldering after 45 minutes (Yes/No)	Transition to open flames (Yes/No)	Result
N. 1	10,0	Yes	No	No	Pass
N. 2	10,0	Yes	No	No	Pass
N. 3	10,0	Yes	No	No	Pass
Repeat test					
N. 4	-	-	-	-	-
N. 5	-	-	-	-	-
N. 6	-	-	-	-	-

Test results

Pass

The uncertainties of measurement of input quantities, extended to a 95 % level of confidence (coverage factor $k=2$), are $\pm 0,2$ seconds and $\pm 0,4$ mm.

This test report is part of a PDF file digitally signed by Franco Bulian on 07/07/21.

*The managing director
Dr. Franco Bulian*


The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise required by standards and technical specifications or agreed with the customer, any declarations of conformity made by CATAS are based on the comparison between results and reference values, where the confidence intervals of the measures are not taken into account. Unless otherwise stated, sampling is made by the customer; in this case the test results are referred to the sample as received.